

## FR-PC RESIN PROCESSING CONDITIONS

Items	Self extinguishing Grade
Grade No.	<b>AC3610</b>
Pre-drying (°C xhr)	110~120°C 4~6hr
Mold Shrinkage (%)	0.5~0.7
Screw Temp. (°C)	260~295
Injection Pressure (Kg/cm <sup>2</sup> )	50~130
Mold Temp. (°C)	80~100

Notes : Products quality from injection process depends on the following factors:

1. Wall thickness of Products
2. Mold cooling loop design
3. Mold gate and runner design



FORMOSA CHEMICALS & FIBRE CORPORATION PLASTICS DIVISION  
HEAD OFFICE: 201, TUNG HWA N. RD., TAIPEI, TAIWAN, R.O.C.  
SERVICE TEL: +886-2-27178405 FAX: +886-2-27131649